

# EXHIBIT 5

Compounds with negligible reactivity with OH Radical

Non-Photocrosslinkable compounds # 4

Zero-volatile organic compounds - chlorine based

<u>Methylene chloride</u> <u>solvent</u>	<u>Solubility</u>	<u>Resins</u> (10 grams)
100 grams/solvent	S	Styrene-Butadiene elastomer
"	S	Styrene "
"	S	Styrene-Isoprene-Styrene "
"	S	Nitrocellulose Coating resin or Ink
"	S	Alkyd "
"	PS	Silicone "
"	PS	Cellulose Acetate Butate "
"	S	Acrylic "
"	S	Terpene Tackifier
"	S	Polyurethane elastomer
"	S	Acrylic ester Tackifier
"	S	Carbazone-Indane "
"	I	PVC Resin
"	S	epoxy "
"	S	Chlorinated Rubber "
"	S	Phenolic "
"	S	Olefin Tackifier
"	S	Vinyl Resin

S = Soluble PS = Partially Soluble

I = Insoluble

C = Cloudy

Good solubility for  
use in Adhesive, Ink or  
Coating Formulations